

## PAR<sup>®</sup> CLAY

June 26, 2007

RTV Product Code: **09500**  
Composition: Hydrated aluminum silicate, kaolin  
Physical State: Cream powder

	<u>Specification</u>	<u>Test Method</u>
*Fineness, retained on 325 mesh	0.7% maximum	T-938
*Moisture Content	1.0% maximum	T-936

### GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Brightness	70
Density at 25°C	2.6 Mg/m <sup>3</sup>
Loss on Ignition	14%

\*Certified Property

*Uses - Reinforcer and inert filler for all elastomers. Used in non-black compounds of all types.*