Tecnoflon® T 636/L

fluoroelastomer

TECNOFLON® T 636/L is a low viscosity fluoroelastomer terpolymer designed to provide improved low temperature characteristics. Tecnoflon® T 636/L does not contain curatives: therefore the proper levels of Tecnoflon® FOR M1 and Tecnoflon® FOR M2 must be added to achieve the required properties. Tecnoflon® T 636/L is a lower viscosity version of Tecnoflon® T 636: please refer to Tecnoflon® T 636 Technical data sheet for data on chemical resistance: Tecnoflon® T 636/L exhibits the same excellent heat and chemical resistance expected from Tecnoflon® copolymers.

Some of the basic properties of TECNOFLON® T 636/L are:

- Improved low temperature performance
- Good heat and chemical resistance
- Very low compression set
- Excellent mould release
- Lack of mould fouling
- Superior mould flow

Tecnoflon® T 636/L can be used for compression, injection and transfer molding of O-rings, diaphragms, gaskets, seals, moulded shapes or other items requiring improved low temperature performance. Tecnoflon® T 636/L can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers. This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting.

Finished goods can be produced by a variety of rubber processing methods.

Click here for full datasheet.

Tecnoflon® T 636/L
fluoroelastomer

General		
Material Status	• Commercial: Active	
Availability	• Europe	• North America
Features	• Chemical Resistant • Good Flow • Good Mold Release • High Heat Resistance	• Low Compression Set • Low Viscosity • Terpolymer
Uses	• Belts/Belt Repair • Blending • Diaphragms • Gaskets • Hose	• Low Temperature Applications • Profiles • Seals • Sheet
Appearance	• Translucent	
Forms	• Slab	
Processing Method	• Calendering • Compounding • Compression Molding	• Extrusion • Injection Molding • Resin Transfer Molding

Physical	Typical Value	Unit
Mooney Viscosity [1] (ML 1+10, 121°C)	22	MU
Fluorine Content [1]	66	%

Notes

Typical properties: these are not to be construed as specifications.

[1] Raw polymer

Tecnoflon® T 636/L
fluoroelastomer

SOLVAY
asking more from chemistry®

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa
SpecialtyPolymers.Americas@solvay.com | Americas
SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.