

# Tecnoflon® VPL 85540 / VPL 55540

## Very Low Temperature Peroxide Curable

Tecnoflon® VPL 85540 and VPL 55540 belong to a brand new generation of very low temperature peroxide curable FKM. They have been designed to offer outstanding low temperature flexibility (i.e.  $TR_{10} = -40\text{ °C}$ ). Like all other Tecnoflon® peroxide curable grades, they exhibit excellent processability and superior mechanical properties and sealing ability; moreover they need very short postcuring cycles.

Some of the basic properties of Tecnoflon® VPL 85540 and VPL 55540 are:

- Outstanding low temperature behavior
- Very good chemical resistance
- Low post cure
- Superior mold flow
- Lack of mold fouling
- Excellent mold release
- Very good chemical resistance

Solvay Specialty Polymers offers medium (VPL 85540) and low viscosity (VPL 55540) versions in order to fulfil all customer's requirements. Accordingly to the curing technology, Tecnoflon® VPL 85540 and VPL 55540 can be transformed by all the molding techniques, including injection, injection compression, compression, and transfer molding.

Tecnoflon® VPL 85540 and VPL 55540 can be used with all typical peroxide curing system and the other fluoroelastomer compounding ingredients. Mixing can be accomplished with two roll mills or internal mixers.

Tecnoflon® VPL 85540 and VPL 55540 can be extruded into hoses or profiles or can be calendered to make sheet stocks or belting.

### Handling and safety

Normal care and precautions should be taken to avoid skin contact, eye contact and breathing of fumes. Smoking is prohibited in working areas. Wash hands before eating or smoking. For complete health and safety information, please refer to the material safety data sheet.

### Basic characteristics of the raw polymer are as follows:

Property	Unit	VPL 55540	VPL 85540	Test Method
ML (1+10') at 121 °C	MU	25	45	ASTM D1646
Fluorine content	%	65	65	Solvay Internal Method – NMR
Specific gravity	$\text{g/cm}^3$	1.83	1.83	ASTM D792
Colour		Translucent	Translucent	
Packaging/Form		Slabs	Slabs	
Solubility		Ketones and esters	Ketones and esters	

# Tecnoflon® VPL 85540 / VPL 55540

Very Low Temperature Peroxide Curable

## Typical properties

Property	Unit	VPL 55540	VPL 85540	Test Method
Tecnoflon®	phr	100	100	
Luperox® 101XL-45	phr	2	2	
Drimix® TAIC (75%)	phr	5	5	
ZnO*	phr	5	5	
N-990 MT Carbon Black	phr	30	30	

Property	Unit	VPL 55540	VPL 85540	Test Method
Mooney viscosity ML (1+10') at 121 °C	MU	28	43	ASTM D1646
<b>MDR 6 min at 160 °C arc 0.5°</b>				ASTM D6601
Minimum torque	lb · in	0.7	1.1	
Maximum torque	lb · in	28.4	27.2	
t <sub>s2</sub>	min	1.1	0.9	
t' <sub>50</sub>	min	2.0	1.9	
t' <sub>90</sub>	min	3.8	3.7	
<b>Post cure: 4 h at 230 °C</b>				
100% Modulus	MPa	7.2	6.9	ASTM D412C
Tensile strength	MPa	15.0	15.8	
Elongation at break	%	172	174	
Hardness	ShoreA	68	67	ASTM D2240
<b>Compression set</b> 25% deformation, 70 h at 200 °C				ASTM D395 method B
O-ring #214	%	21	20	
<b>Temperature retraction</b>				ASTM D1329
TR <sub>10</sub>	°C	-40	-40	

# Tecnoflon® VPL 85540 / VPL 55540

Very Low Temperature Peroxide Curable

## Fuel resistance

Property	Typical Value	Unit	Test Method
<b>Fuel B, 70 h at 24°C</b>			
Δ Tensile strength	-15	%	
Δ Elongation at break	4	%	
Δ Hardness	-4	Shore A	
Δ Volume	4	%	
<b>Fuel C, 168 h at 23°C</b>			
Δ Tensile strength	-20	%	
Δ Elongation at break	-8	%	
Δ Hardness	-4	Shore A	
Δ Volume	8	%	
<b>Fuel C, 168 h at 40°C</b>			
Δ Tensile strength	-31	%	
Δ Elongation at break	-21	%	
Δ Hardness	-6	Shore A	
Δ Volume	12	%	
<b>M15, 168 h at 23°C</b>			
Δ Tensile strength	-66	%	
Δ Elongation at break	-34	%	
Δ Hardness	-9	Shore A	
Δ Volume	16	%	
<b>Fuel CE 10, 70 h at 60°C</b>			
Δ Tensile strength	-50	%	
Δ Elongation at break	-23	%	
Δ Hardness	-10	Shore A	
Δ Volume	19	%	
<b>Fuel CE 22, 70 h at 60°C</b>			
Δ Tensile strength	-47	%	
Δ Elongation at break	-23	%	
Δ Hardness	-10	Shore A	
Δ Volume	21	%	
<b>Fuel CE 85, 70 h at 60°C</b>			
Δ Tensile strength	-39	%	
Δ Elongation at break	-13	%	
Δ Hardness	-7	Shore A	
Δ Volume	11	%	

# Tecnoflon® VPL 85540 / VPL 55540

Very Low Temperature Peroxide Curable

Property	Typical Value	Unit	Test Method
<b>Ethanol, 168 h at 40°C</b>			
Δ Tensile strength	-34	%	
Δ Elongation at break	-9	%	
Δ Hardness	-5	Shore A	
Δ Volume	7	%	
<b>RME, 336 h at 150°C</b>			
Δ Tensile strength	-16	%	
Δ Elongation at break	-2.4	%	
Δ Hardness	-3	Shore A	
Δ Volume	1.5	%	
<b>B20 (Diesel + 20% RME), 1,008 h/150°C</b>			
Δ Tensile strength	-14	%	
Δ Elongation at break	26	%	
Δ Hardness	-12	Shore A	
Δ Volume	20	%	
<b>Fam B, 72 h at 60°C</b>			
Δ Tensile strength	-39	%	
Δ Elongation at break	-31	%	
Δ Hardness	-7	Shore A	
Δ Volume	21	%	
<b>PN 180, 336 h at 60°C</b>			
Δ Tensile strength	-41	%	
Δ Elongation at break	-6	%	
Δ Hardness	-15	Shore A	
Δ Volume	22	%	

# Tecnoflon® VPL 85540 / VPL 55540

Very Low Temperature Peroxide Curable

## Oil resistance

Property	Typical Value	Unit	Test Method
<b>Dexron VI ATF, 1,500 h at 150 °C</b>			
Δ Tensile strength	-19	%	
Δ Elongation at break	-13	%	
Δ Hardness	0	Shore A	
Δ Volume	1	%	
<b>ATF94, 1,500 h at 150 °C</b>			
Δ Tensile strength	-16	%	
Δ Elongation at break	-11	%	
Δ Hardness	1	Shore A	
Δ Volume	1	%	
<b>ASTM 105G (SF 105), 500 h at 150 °C</b>			
Δ Tensile strength	-15	%	
Δ Elongation at break	-2	%	
Δ Hardness	-2	Shore A	
Δ Volume	1	%	
<b>PN 180, 168 h at 150 °C</b>			
Δ Tensile strength	-10	%	
Δ Elongation at break	2.6	%	
Δ Hardness	0	Shore A	
Δ Volume	1.6	%	
<b>Reference oil 300, 500 h at 150 °C</b>			
Δ Tensile strength	-8	%	
Δ Elongation at break	6	%	
Δ Hardness	-6	Shore A	
Δ Volume	7	%	
<b>Havoline XLC/Water 50:50, 1,000 h at 130 °C</b>			
Δ Tensile strength	-24	%	
Δ Elongation at break	-6.1	%	
Δ Hardness	0	Shore A	
Δ Volume	1.5	%	
<b>Diethanolamine 1% (water), 70 h at 140 °C</b>			
Δ Tensile strength	-12	%	
Δ Elongation at break	5	%	
Δ Hardness	-1	Shore A	
Δ Volume	4	%	

# Tecnoflon® VPL 85540 / VPL 55540

Very Low Temperature Peroxide Curable

Property	Typical Value	Unit	Test Method
<b>Steam, 168 h at 200 °C</b>			
Δ Tensile strength	-16	%	
Δ Elongation at break	18	%	
Δ Hardness	0	Shore A	
Δ Volume	0.2	%	
<b>MILH83282, 70 h at 135 °C</b>			
Δ Tensile strength	-13	%	
Δ Elongation at break	12	%	
Δ Hardness	-3	Shore A	
Δ Volume	2	%	

[www.solvay.com](http://www.solvay.com)

[SpecialtyPolymers.EMEA@solvay.com](mailto:SpecialtyPolymers.EMEA@solvay.com) | Europe, Middle East and Africa

[SpecialtyPolymers.Americas@solvay.com](mailto:SpecialtyPolymers.Americas@solvay.com) | Americas

[SpecialtyPolymers.Asia@solvay.com](mailto:SpecialtyPolymers.Asia@solvay.com) | Asia Pacific



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products. Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks are property of the companies that comprise Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved. R 11/2019 | Version 2.2 Design by ahlersheinel.com