

VISTAMAXX™

Specialty Elastomers
Effective October 1, 2007

Vistamaxx 6102

Sales Specification

Property	Test Method ¹	Unit	Value
Melt Flow Rate (230°C, 2.16 kg)	ASTM D 1238	Gm/10 min.	3 ± 1.5
Ethylene Content	ASTM D 3900 A or B	wt %	16 ± 1
Color, Hunter B	ASTM D 6290	Hunter B	2 max.

¹ ExxonMobil test methods are available upon request