Vanderbilt Chemicals, LLC A Wholly Owned Subsidiary of R.T. Vanderbill Holding Company, Inc. 30 WINFIELD STREET, PO. BOX 5150, NORWALK, CONNECTICUT 06856-5150 • (203) 853-1400 Fax (203) 853-1452 • Internet Address: www.waterbiltchemicals.com

Specification

BUTYL ZIMATE[®] DUSTLESS

August 26, 2014

RTV Product Code:**74804**Composition:Zinc dibutyldithiocarbamatePhysical State:White to cream powder

	Specification	Test Method
*Fineness, through 100 mesh	99.9% minimum	T-14
*Melting Range	103-110°C	T-3D
*Heat Loss 2 hrs. @ 60-65°C	0.5% maximum	T-1A
*Zinc Content	13.0 - 15.0%	T-365, AA-44

GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Anti-Dusting Agent	0.4%
Density at 25°C	1.21 Mg/m ³

Solubility - Soluble in chloroform, gasoline, and toluene. Insoluble in water.

*Certified Property

Uses - Accelerator for EPDM and natural and synthetic latexes. Functions as a non-discoloring antioxidant in non-curing applications, and as a stabilizer in IIR. Also used as an antioxidant in thermoplastic rubbers and hot melts.

Standard Container - 50 pound multi-wall paper bag, 125 pound fiber drum

ZIMATE is a registered trademark of R.T. Vanderbilt Holding Company, Inc. and/or its respective wholly owned subsidiaries.

The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all –inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. Vanderbilt Chemicals, LLC does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent or to violate any federal, state or local law or regulation.